

FLOORTOP 2K

TWO PART SELF LEVELLING UNDERLAYMENT



DESCRIPTION

FLOORTOP 2K is a free flowing and self levelling two components specially designed for easy application over concrete floors as an underlayment for subsequent placement of floor coverings. It is formulated to incorporate a state of art acrylic polymer technology which provides excellent flexible, smooth self levelling compound to be applied at a thickness from featheredge to 10 mm.

FEATURES & BENEFITS

- Flowable consistency for self levelling applications.
- Pumpable through standard equipment.
- Self levelling for smooth , flat floors.
- Minimal shrinkage for outstanding resistance to cracking.
- Improved flexibility.

BASIC USES

- Placement over wood, tile or terrazzo.
- Smooth concrete surfaces.
- Re-level worn floors.
- Flooring underlayment.
- Levelling course under ceramic tile.
- Hospitals – hotel floors prior to carpeting, an vinyl flooring.

TECHNICAL INFORMATION

The following results at 28 days developed under laborating conditions.

Compressive strength

ASTM C 109 (m) - 30 mPa

Bond strength

ASTM C 1042 - 8 mPa

Flexural strength

ASTM C 348 - 10 mPa

DIRECTION FOR USE

Surface preparation

New concrete must be a minimum of 3 days old and must be broom textured at the time of placement to secure a good mechanical bond for the underlayment. If the new concrete is not finished with an appropriate texture, follow surface preparation procedures of old concrete. Old concrete must be clean and textured. All oil,dirt, debris, paint and unsound concrete must be removed. The surface must be prepared mechanically using a scabblor, bush hammer, shotblast or scarifier which will give a surface profile to coarse sandpaper. The final step in cleaning should be the complete removal of all residues with vacuum cleaner or pressure washing.

Acid etching is acceptable only when mechanical preparation is impractical. It is recommended that only contractors experienced in the acid etching process use this means of surface preparation. The salts of the reaction must be thoroughly washed away. Allow the concrete to completely dry.

Note

Even with proper procedures, an acid etched surface may not provide a bond as strong as those which are mechanically prepared. All concrete must possess an open surface texture with all curing compounds and sealer removed.

Mixing

Small quantities may be mixed with a drill and "jiffy" mixer. Use paddle type mortar mixer for large jobs. Add the appropriate amount of mixing liquid for the batch size and add the dry product. Mix for a minimum of 3 minutes to obtain lump free homogeneous mix. The mixed product should be quickly transported to the repaired area and placed immediately.

Placement

The product must be continuously placed to provide a smooth and uniform surface. Start in one corner placing a continuous stream of material along one edge of the area and back lap as soon as possible for a uniform, smooth surface. Tools such as spiked rollers, notched squeegees, trowels and smoothers may be used to assist placement.

Finishing

This product is self-levelling and requires no finishing or trowelling operation.

Curing

FLOORTOP 2K does not require curing with standard methods for most applications. Under hot windy or rapid drying conditions, a fog spray or wet cure for 24 hours is recommended after the final set of material.

CLEAN-UP

Clean all tools and equipments with water before the material hardens

PRECAUTIONS / LIMITATIONS

- Designed for interior use
- Do to use exterior application or in areas continuously subjected to moisture or water.
- Do not use FLOORTOP 2K wearing surface for industrial floors.
- Store in dry place.

COVERAGE	Each unit of FLOORTOP 2K covers 4.1 M ² at average thickness of 5 mm
PACKAGING / YIELD	FLOORTOP 2K is packaged in units containing 30 kg of powder and 8.1 liters of FLOORTOP 2K LIQUID. Yield is 21 liters.
COLOR	Contact CMCI Tech Dept.

Quality Statement

CMCI manufactures its products at their manufacturing facility in Saudi Arabia as per the Quality Procedures certified to conform with quality Management System described in ISO 9000 series

CMCI provides a comprehensive technical support system for its full range of high performance construction products CMCI also offers full technical field support to consultants, Architects, contractors, applicators and End Users.

The Technical Specification information and recommendations given are based on the current technical knowledge and the user or his representative is recommended to check the suitability of the product CMCI reserves the right to amend the technical characteristic of the product as part of ongoing research and development. As the work execution is beyond the direct and continuous control of CMCI no guaranty and or responsibility is assumed on the performance of work completion executed with use of our products.

"High Quality Construction Chemicals"
CONSTRUCTION MATERIAL CHEMICAL INDUSTRIES
P.O. Box 7137, Dammam 31462, Saudi Arabia,
Tel: 00966-13-8471450; Fax: 00966-13-8471575
Email: tech@cmci-sa.com, Web: www.cmci-sa.com